

Test Report No.: SHAHL24011837801 **Date:** Jun 11, 2024 Page 1 of 3

Client Name: NUOXIN NEW MATERIALS (SHANDONG) CO., LTD

Client Address: ROOM 0709, BUILDING 8, XINTIANDI, SHANGANG, JINAN AREA, CHINA (SHANDONG)

PILOT FREE TRADE ZONE

Sample Description: BLACK MASTERBATCH

Style No.: LA-1+

Manufacturer: QINGYUN NUOXIN PLASTIC NEW MATERIALS CO., LTD Supplier: QINGYUN NUOXIN PLASTIC NEW MATERIALS CO., LTD

Origin of the Product(s): CHINA

The above sample(s) and information were provided by the client.

SGS No.: SHHL2406029364CW

Sample Receiving Date: Jun 03, 2024

Testing Period: Jun 03, 2024 ~ Jun 11, 2024

Test Requested: Select test(s) as requested by the client.

Testing Performed: Follow selected test(s) as requested by client.

	Test Requirement	Comment
1	US FDA 21 CFR 177.1520 - Density at 23°C	Fail
2	US FDA 21 CFR 177.1520 - Extractable fraction	Pass
3	US FDA 21 CFR 177.1520 - Soluble fraction in Xylene	Fail

Signed for and on behalf of SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd.

Danna Ji

Danna Ji

Approved Signatory



Verification: check.sgsonline.com.cn



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Cond

3rdBuilding,No.889 Yishan Road Xuhui District,Shanghai China 200233

e ens china@ens com



Test Report No.: SHAHL24011837801 **Date:** Jun 11, 2024 Page 2 of 3

Test Result(s):

Test Part Description:

SN ID	I ID Sample No. SGS Sample ID		Description	Material (claimed by the client)
SN1	A1	SHA24-0118378-0001.C001	Black plastic particle	PE

Remarks:

(1) mg/dm² = milligram per square decimeter mg/inch² = milligram per square inches μg/cm² = microgram per square centimeter mg/L = milligram per litre mg/kg = milligram per kilogram

(2) °C = degree Celsius

°F = degree Fahrenheit

(3) <= less than

(4) RL = Reporting Limit

(5) ND = Not Detected (< RL).

US FDA 21 CFR 177.1520 - Density at 23°C

Test Method: With reference to US FDA 21 CFR 177.1520d(1).

Test Item(s)	Limit	Unit(s)	A1
Density at 23°C	0.85-1.00	g/cm³	1.196#
Comment			Fail

US FDA 21 CFR 177.1520 - Extractable fraction

Test Method: With reference to US FDA 21 CFR 177.1520(d)(3)(ii).

Simulant used	Test Condition	Limit	Unit(s)	RL	A1	Comment
n-Hexane	50°C, 2 hrs	5.5	%(w/w)	0.1	2.5	Pass

US FDA 21 CFR 177.1520 - Soluble fraction in Xylene

With reference to US FDA 21 CFR 177.1520(d)(4)(ii). Test Method:

Test Item(s)	Limit	Unit(s)	RL	A1
Soluble Fraction in Xylene	11.3	%(w/w)	0.5	12.3#
Comment				Fail

Remark: # = Exceed the limit.

Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="https://www.sgs.com/en/Terms-and-Conditions/Terms-and-Con


3rdBuilding,No.889 Yishan Road Xuhui District,Shanghai China 200233

t E&E (86-21) 61402553 f E&E (86-21)64953679 www.sgsgroup.com.cn t HL (86-21) 61402594 f HL (86-21) 61156899



Test Report No.: SHAHL24011837801 **Date:** Jun 11, 2024 Page 3 of 3

Sample Photo:



SGS authenticate the photo on original report only

*** End of Report ***



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="https://www.sgs.com/en/Terms-and-Conditions/Terms-and-Con

or email: <u>CN.Doccheck@sgs.com</u>
[3stBuilding,No.889 Yishan Road Xuhui District,Shanghai China 200233 t E&E (86–21) 61402553 f E&E (86–21)64953679 www.sgsgroup.com.cn

中国・上海・徐汇区宜山路889号3号楼 邮编: 200233 tHL(86-

t HL (86-21) 61402594 f HL (86-21)61156899

e ens china@ens com